

310 Stainless Steel

310 STAINLESS STEEL DATASHEET

310 provides good malleability and weldability with superb high temperature properties. Because of these superb high temperature properties, 310 is often used in furnace parts, oil burner parts, carburizing boxes, heat treatment baskets and jigs, heat exchangers and welding filler wire and electrodes. Even though it is not typically used in cryogenic environments, it remains exceedingly tough in cryogenic temperatures. On the Rockwell B hardness scale, 310 has a hardness of 95. 310 provides excellent resistance to corrosion because of its high chromium content.

Common industry/applications are: Flare tips, Tube hangers for petroleum refining and steam boilers, Coal gasifier internal components, Food processing equipment, Refractory anchor bolts, Burners, and combustion chambers

Product forms include Reducers, Flanges, Pipe, Plate, Round Bar, Sheet, and Tubing.

Standards


- UNS S31008
- ASTM A240
- ASTM A276/A479
- AMS 5521
- AMS 5651
- ASME AS-240/SA-479

Physical Properties

- Density: 0.285LB/in³ (7.89g/cm³)
- Melting Point: 2470–2555°F (1354–1402°C)
- Modulus of Elasticity: 28.5x10⁶psi (196 GPa)

Characteristics

- Oxidation resistance to 2000°F
- Moderate strength at high temperature
- Resistance to hot corrosion
- Strength and toughness at cryogenic temperatures



Chemical Composition

	C	Mn	S	P	Si	Cr	Ni	Cu	Mo
MIN	-	-	-	-	-	24.00	19.00	-	-
MAX	0.08	2.00	0.03	0.45	0.75 *	26.00	22.00	0.50	0.75

*ASTM specification 1.50 max Si.

Mechanical Properties

Tensile (min) KSI (Mpa)	Yield (min) KSI (Mpa)	Elongation (min) %	Reduction of Area (min) %	Hardness HRB (BHN)
80 (550)	35 (245)	45%	50%	95 (217) Min.

Mechanical properties can be altered (increased/decreased) by the addition of other chemical elements like Selenium (Se) to form 303Se. However, these grades are more specialized and may not be available in all forms and sizes.

WWW.SPECIALTYSTEELSUPPLY.COM



SPECIALTY STEEL SUPPLY
19201 CIRCLE LAKE DR
PINEHURST, TX 77362
Call for a quote (281) 821-7111



All information in our data sheet is based on approximate testing and is stated to the best of our knowledge and belief. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of trading.
© Specialty Steel Supply