INCONEL®718 NACE Nickel Alloy

INCONEL® 718 NACE is a variant of the 718 nickel alloy. It is produced with a modified chemical composition and which has been age-hardened. It is produced specifically in a way to ensure it meets the maximum hardness requirements of NACE MR0175 for use in sour gas H₂S service. 718 NACE has good corrosion resistance and weldability, combined with high strength while having lighter tolerances on the hardness. Properties are typical and are not required to be reported in the Annealed condition. Typically, 440C is purchased in an annealed condition and then machined prior to heat treating as material can be hardened to 50-60HRC.

Can be used in various industry/applications based on the desired condition and application use. Common industry/applications are: Sour Gas, Oil and Gas, Aerospace, Rockets and Spacecraft and Fasteners.

API 6ACR/718

Product forms include round bar and forgings.

Standards

- **UNS N07718**
- ASTM B637
- NACE MR0175

Physical Properties

- Density: 0.297LB/in3 (8.22g/cm3)
- Melting Point: 2160-2440°F (1182-1337°C)
- Modulus of Elasticity: 29.0x10^epsi (200 GPa)

Characteristics

- Good corrosion and heat resistance.
- Suitable for use Good corrosion resistance.
- Capable of various Quench & Tempers.

Chemical Composition

	С	Mn	S	Р	Si	Мо	Ti	AI	Cu	Cr	Ni *	Со
MIN	-	-	-	-	-	2.80	0.80	0.40	-	17.00	50.00	-
MAX	0.045	0.35	0.01	0.01	0.35	3.30	1.15	0.60	0.23	21.00	55.00	1.00

* Niobium (aka Columbium) + Tantalum (Nb+Ta) = 4.87-5.20 Other: Pb: 1000pppm, Se: 0.0005ppm, Bi: 50ppm & Mg: 0.0006ppm

Mechanical Properties									
	Tensile KSI (Mpa)	Yield KSI (Mpa)	Elongation %	Reduction of Area % *	Hardness HRC (BHN)				
MIN	150 (1034)	120 (827)	20%	35/25	32 (298)				
MAX	-	145 (1000)	20%	35/25	40 (363)				

RoA Values: ≤10" diameter / >10" diameter

Size in (mm)	Orientation	Temp °F (°C)	Min Avg Ft-Lbs (J)	Min Single Ft-Lbs (J)	Lateral Expansion in (mm)
<3 (76)	Longitudinal	-75 (-60)	50 (68)	45 (61)	0.015 (0.38)
≥3 (76) - ≤10 (254)	Transverse	-75 (-60)	35 (47)	30 (41)	0.015 (0.38)
>10 (254)	Transverse	-75 (-60)	30 (41)	27 (37)	0.015 (0.38)



All information in our data sheet is based on approximate testing and is stated to the best of our knowledge and belief. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of trading. © Specialty Steel Supply





SPECIALISTS IN LONG BARS AND HEAVY PLATE



