

A-286 Stainless Steel

A-286 STAINLESS STEEL DATASHEET

A-286 stainless steel is a precipitation-hardenable super-alloy based on iron. A-286 stainless steel finds use in applications requiring high strength, paired with corrosion resistance up to 1300 °F (700 °C). A-286 stainless steel has other favorable properties, including excellent fabrication characteristics, low-temperature non-magnetic strength [down to -320 °F (-196 °C)], and ductility.

A-286 stainless steel finds use in various aircraft components, including jet engine components, fasteners, and springs. Moreover, A-286 stainless steel is used in industrial gas turbines, aqueous solutions with moderate corrosion properties, and non-magnetic cryogenic parts. Other applications for A-286 stainless steel include high-temperature afterburner parts, tanks, piping, pumps, heat exchangers, and superchargers in the automotive industry.

Product forms include pipe, tube, fitting, flange, sheet, strip, plate, round bar, flat bar, fastener, forging stock, and hexagon.



Standards

- UNS S66286

Physical Properties

- Density: 0.286 LB/in³ (7.92 g/cm³)
- Melting Point: 2500–2690°F (1370–1430°C)
- Modulus of Elasticity: 28.8x10⁶psi (199 GPa)
- Magnetic Permeability: 1.010 Max

Characteristics

- excellent fabrication characteristics, low-temperature non-magnetic strength [down to -320 °F (-196 °C)], and ductility.

Chemical Composition

	C	Mn	S	P	Si	Cr	Ni	Ti	Mo	V	Al	B	Fe
MIN	-	-	-	-	-	13.50	24.00	1.90	1.00	0.10	-	0.003	-
MAX	0.08	2.00	0.025	0.025	1.00	16.00	27.00	2.30	1.50	0.50	0.35	0.010	balance

Mechanical Properties

Tensile (min) KSI (Mpa)	Yield (min) KSI (Mpa)	Elongation (min) %	Reduction of Area (min) %	Hardness HRC (BHN)
89 (620)	39 (275)	40%	20%	32 (304) Min.

WWW.SPECIALTYSTEELSUPPLY.COM



SPECIALTY STEEL SUPPLY
19201 CIRCLE LAKE DR
PINEHURST, TX 77362
Call for a quote (281) 821-7111



All information in our data sheet is based on approximate testing and is stated to the best of our knowledge and belief. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of trading.
© Specialty Steel Supply