

F55 (25Cr) Duplex Stainless Steel

F55 (25Cr) DUPLEX STAINLESS STEEL DATASHEET

F55 (25Cr) Duplex Stainless Steel (also known as Zeron 100) Super Duplex is an austenitic-ferritic (duplex) stainless steel. Consisting of 25% Chromium and 7% Nickel. A main difference in F55 (25Cr) Duplex Stainless Steel over F53 (2507) is the inclusion of Tungsten in the chemical composition.

The intentional addition of Tungsten is to improve corrosion resistance similar to that of Molybdenum. Like other duplex grades F55 (25Cr) Duplex Stainless Steel combines high corrosion resistance and strength over austenitic stainless steels, while also having superior pitting resistance. F55 (25Cr) Duplex Stainless Steel does suffer from embrittlement and loss of toughness, when exposed to prolonged use in applications or environments below -50°F or above +600°F, this is why duplex is not suitable for exposure outside of these ranges.

Common industry/applications for F55 (25Cr) Duplex Stainless Steel include oil & gas equipment, chemical and biofluid processing, pressure vessels, and mechanical and structural.

Product forms include round bar, plate & sheet, and forgings.

Standards

- UNS S32760

Physical Properties

- Density: 0.285LB/in³ (7.88g/cm³)
- Melting Point: 2525–2630°F (1385–1443°C)
- Modulus of Elasticity: 29.0x10⁶psi (200 GPa)
- Magnetic Permeability: <1.05 @ 68°F (20°C)

Characteristics

- For use in -50F to +600F temperatures.
- Excellent corrosion & pitting resistance.
- Good cryogenic (-50F) impact strength.



Chemical Composition

	C	Mn	S	P	Si	Cr	Ni	Mo	N	W	Cu
MIN	-	-	-	-	-	24.00	6.00	3.00	0.20	0.50	0.50
MAX	0.03	1.00	0.01	0.03	1.00	26.00	8.00	5.00	0.30	1.00	1.00

PREN: Pitting Resistance Equivalent Number: An Equation to correlate pitting resistances of product, based on chemistry. This equation is: $Cr + (3.3 \times Mo) + (16 \times N) - PREN = >40$

Mechanical Properties: Wrought & Forged Bars

Tensile (min) KSI (Mpa)	Yield (min) KSI (Mpa)	Elongation (min) %	Reduction of Area (min) %	Hardness HRB (BHN)
100 (758)	80 (551)	25%	45%	28-33 (270-311)

Typical mechanical properties, actual minimums may vary based on processing.

WWW.SPECIALTYSTEELSUPPLY.COM



SPECIALTY STEEL SUPPLY
19201 CIRCLE LAKE DR
PINEHURST, TX 77362
Call for a quote (281) 821-7111



All information in our data sheet is based on approximate testing and is stated to the best of our knowledge and belief. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of trading.
© Specialty Steel Supply